



PRODUCT NO. 5202

ASPHALT RESATURANT

DESCRIPTION:

- Fortress® Asphalt Resaturant is a balanced blend of premium oxidized asphalt and penetrating oils, further augmented with quality non-asbestos reinforcing fillers.
- It provides rejuvenating qualities to weathered asphalt BUR systems.

FEATURES:

- Cold applied by brush, squeegee or airless spray equipment.
- Eliminates the use of kettles and open flames.
- Rejuvenates aged asphalt flood coats and restores many of it's original properties
- Reseals cracks and other imperfections in the flood coat, extending the life of the roof system.
- Meets current Volatile Organic Compounds (VOC) regulations.
- Non-Asbestos

USES:

- Rejuvenates aged asphalt food coats..
- Resaturates weathered and exposed roofing felts and fabrics..

APPLICATION:

- Ready to apply. Do not heat. Do not thin.

SURFACE PREPARATION:

- All work surfaces must be clean, dry, free of dirt, dust, debris, oils, loose and/or embedded gravel, un-adhered coatings, deteriorated membranes, and other contaminants that may result in a surface that is not sound.
- All necessary repairs must be completed before application to ensure the optimum performance.
- All surfaces must be free of frost, snow and ice.

APPLICATION DIRECTIONS:

- Apply at a rate of approximately 4-8 gallons per square. Then, re-embed gravel.

APPLICATION PRECAUTIONS:

- **DO NOT** use with or on 100% rubber or plastic substrates.
- **DO NOT** use on or with products containing coal tar.
- **DO NOT** apply to damp or wet surfaces.
- **DO NOT** use where this product may come in contact with potable water.
- **DO NOT THIN.**
- **EXTERIOR USE ONLY.**

CLEAN UP:

- Immediately rinse/flush equipment and tools with mineral spirits after use, exercising all flammable liquid precautions.
- Use waterless hand cleaner on skin.

TYPICAL PROPERTIES:

Property	Test Method	Result
Wt/gal, lbs.	D6511	8.5-9.0
Solids, % by wt.	D6511	75-80
% by vol.		70-75
Viscosity, grams	Stormer @ 200 rpm	700-1100
pH		N/A
Flash Point, °F	PMCC	105 min.
Color, Cured	Visual	Black
Drying time, Touch	70 °F/50% R.H.	1 hour
Shelf Life	70°F/50% R.H.	1 year
VOC	EPA Method 24A	300 gm/liter max.

PACKAGING:

- 5-gallon pails (46 lbs.) and 55-gallon drums (518 lbs.)

SPECIFICATION COMPLIANCES:

- none

SAFETY AND ENVIRONMENTAL PRECAUTIONS:

- **CONSULT MATERIAL DATA SAFETY SHEET FOR DETAILED HANDLING AND DISPOSAL**