



**PRODUCT NO.
5205**

FIBERED ASPHALT ROOF COATING

DESCRIPTION:

- A special blend of oxidized bitumens, petroleum distillates and non-asbestos fillers and reinforcing fibers.
- Fibered Asphalt Coating preserves and protects BUR, modified bitumen membranes, metal and concrete surfaces.

FEATURES:

- Cold applied by brush, squeegee or airless spray equipment.
- Eliminates the use of kettles and open flames.
- Preserves surfaces from costly deterioration, extending the useful service life of the roof system.
- Non-Asbestos
- ASTM D4479, Metro Dade, UL Classified for material characteristics.

USES:

- A protective coating/barrier over BUR, modified bitumen membranes and metal roofs.
- As a flood coat for receiving aggregate.

APPLICATION:

- Ready to apply. Do not heat. Do not thin.

SURFACE PREPARATION:

- All work surfaces must be clean, dry, free of dirt, dust, debris, oils, loose and/or embedded gravel, un-adhered coatings, deteriorated membranes, and other contaminants that may result in a surface that is not sound.
- All necessary repairs must be completed before application to ensure the optimum performance.
- Extremely dusty or dry surfaces should be primed with Fortress® # 5302 Asphalt Primer or Fortress® #5085 HydroPrime™ 200.

APPLICATION DIRECTIONS:

- Apply to the properly prepared surface at a rate of 1-3 gallons per square, if used as a protective coating.
- For use as a flood coat to receive gravel, apply at a rate of approximately 5-8 gallons per square and re-embed gravel.

APPLICATION PRECAUTIONS:

- **DO NOT** use with or on 100% rubber or plastic substrates.
- **DO NOT** use on or with products containing coal tar.
- **DO NOT** apply to damp or wet surfaces.
- **DO NOT** use where this product may come in contact with potable water.
- **DO NOT THIN.**
- **EXTERIOR USE ONLY.**

CLEAN UP:

- Immediately rinse/flush equipment and tools with mineral spirits after use, exercising all flammable liquid precautions.
- Use waterless hand cleaner on skin.

TYPICAL PROPERTIES:

Property	Test Method	Result
Wt/gal, lbs.	D6511	8.2-8.7
Solids, % by wt.	D6511	73-80
% by vol.		72-78
Viscosity, grams	Stormer @ 200 rpm	50-200
pH		N/A
Flash Point, °F	PMCC	105 min.
Color, Cured	Visual	Black
Drying time, Touch	70 °F/50% R.H.	1 hour
Shelf Life	70°F/50% R.H.	1 year
VOC	EPA Method 24A	300 gm/liter max.

PACKAGING:

- 5-gallon pails (45 lbs.) and 55-gallon drums (500 lbs.)

SPECIFICATION COMPLIANCES:

- ASTM D4479, Metro Dade, UL Classified for material characteristics

SAFETY AND ENVIRONMENTAL PRECAUTIONS:

- **CONSULT MATERIAL DATA SAFETY SHEET FOR DETAILED HANDLING AND DISPOSAL**